

Slam Dunk Gym Finish Procedure

1. To remove old coating (omit if applying 'Slam Dunk Gym Finish' over existing stable coating), sand floor with Drum sander or use a floor machine with a 60 to 100 grit screen equivalent. After previous step (or if previous step omitted because coating over existing, stable coating), fine screen the floor with 120 to 280 grit. Inspect floor to ensure proper preparedness and repeat any necessary procedures as and if required.
2. Dust mop the floor with an untreated dust mop, Then tack the floor with a tack cloth and clean with Can-Do cleaner at 1:128 dilution. (Use an autoscrubber if available)
3. Apply three coats of Slam Dunk Gym Finish'. Coverage should be approximately: 1st coat =700 to 900 sq. ft per gallon. 2nd coat = 1000 to 1200 sq.ft. per gallon. 3rd and subsequent coats = 1,500 to 1,800 sq. ft. per gallon. Allow 45 to 60 minutes (or until completely dry) between coats.
4. Apply 'Slam Dunk Finish' with the grain with a lint free, hard string mop, lambs wool applicator, electric sprayer, or a professional wax applicator. Certain types of professional wood floor finish applicators may produce excessive foam during application.
5. For routine maintenance, dust mop floor with a synthetic untreated dust mop and clean with Can-Do Cleaner diluted at 1:128 to 1:64 (1 to 2 oz per gallon, 8-16 ml per liter) with a clean dedicated mop. Periodically scrub and recoat as required.

Important Note: Do not flood floor for stripping or cleaning procedures.